

SSPC: The Society for Protective Coatings

SURFACE PREPARATION SPECIFICATION NO. 1

Solvent Cleaning

1. Scope

1.1 This specification covers the requirements for the solvent cleaning of steel surfaces.

2. Definition

2.1 Solvent cleaning is a method for removing all visible oil, grease, soil, drawing and cutting compounds, and other soluble contaminants from steel surfaces.

2.2 It is intended that solvent cleaning be used prior to the application of paint and in conjunction with surface preparation methods specified for the removal of rust, mill scale, or paint.

3. Surface Preparation Before and After Solvent Cleaning

3.1 Prior to solvent cleaning, remove foreign matter (other than grease and oil) by one or a combination of the following: brush with stiff fiber or wire brushes, abrade, scrape, or clean with solutions of appropriate cleaners, provided such cleaners are followed by a fresh water rinse.

3.2 After solvent cleaning, remove dirt, dust, and other contaminants from the surface prior to paint application. Acceptable methods include brushing, blow off with clean, dry air, or vacuum cleaning.

4. Methods of Solvent Cleaning

4.1 Remove heavy oil or grease first by scraper. Then remove the remaining oil or grease by any of the following methods:

4.1.1 Wipe or scrub the surface with rags or brushes wetted with solvent. Use clean solvent and clean rags or brushes for the final wiping.

4.1.2 Spray the surface with solvent. Use clean solvent for the final spraying.

4.1.3 Vapor degrease using stabilized chlorinated hydrocarbon solvents.

4.1.4 Immerse completely in a tank or tanks of solvent. For the last immersion, use solvent which does not contain detrimental amounts of contaminant.

4.1.5 Emulsion or alkaline cleaners may be used in place of the methods described. After treatment, wash the surface with fresh water or steam to remove detrimental residues.

4.1.6 Steam clean, using detergents or cleaners and follow by steam or fresh water wash to remove detrimental residues.

5. Inspection

5.1 All work and materials supplied under this specification shall be subject to timely inspection by the purchaser or his authorized representative. The contractor shall correct such work or replace such material as is found defective under this specification. In case of dispute the arbitration or settlement procedure established in the procurement documents, if any, shall be followed. If no arbitration or settlement procedure is established, the procedure specified by the American Arbitration Association shall be used.

5.2 The procurement documents covering work or purchase should establish the responsibility for testing and for any required affidavit certifying full compliance with the specification.

6. Safety

6.1 All safety requirements stated in this specification and its component parts apply in addition to any applicable federal, state, and local rules and requirements. They also shall be in accord with instructions and requirements of insurance underwriters.

7. Notes*

7.1 While every precaution is taken to ensure that all information furnished in SSPC standards and specifications is as accurate, complete, and useful as possible, SSPC cannot assume responsibility nor incur any obligation resulting from the use of any materials, coatings, or methods specified herein, or of the standard itself.

7.2 A Commentary Section is available and contains additional information and data relative to this specification. The Surface Preparation Commentary, SSPC-SP COM, is not part of this specification. The table below lists the subjects discussed relevant to solvent cleaning and appropriate Commentary Section.

SSPC-SP 1
November 1, 1982
Editorial Changes September 1, 2000

Subject	SSPC-SP COM Section
Solvents and Cleaners	5.1.1 through 5.1.3
Steam Cleaning	5.1.4
Threshold Limit Values.....	5.1.5
Film Thickness	10

*Notes are not requirements of this specification.