



HEMPADUR MULTI-STRENGTH 35530

35530 : BASE 35539 : CURING AGENT 95530

Description:	HEMPADUR MULTI-STRENGTH 35530 is a solvent-free, two-component, high-build, polyamine cured epoxy paint, which cures to a coating with good resistance to fresh water, sea water, crude oil, and to abrasion. Applicable in thick coats by standard heavy duty airless spray equipment. Harmless to grain cargo.
Recommended use:	As a heavy duty coating on steel exposed to abrasion where solvent-free materials are required. Full colour retention will be of secondary importance. If solvent containing paints are accepted, HEMPADUR MULTI-STRENGTH 45751 substitutes. As a lining in potable water tanks and pipelines. Please see Certificates/Approvals. For application in warm climates. Please see APPLICATION CONDITIONS overleaf.
Service temperature:	Maximum, dry exposure only: 140°C/284°F. In water (no temperature gradient): 35°C/95°F
Certificates/Approvals:	Approved by WRAS for potable water up to 23°C/73°F. Approved by Ministry of Electricity & Water, Bahrain, for potable water. Certified to NSF standard 61 by NSF international for use in potable water tanks with volumes of 100 gallon/380 litres or greater, pipes at 8 inches (20 cm) or greater Tested for non-contamination of grain cargo at the Newcastle Occupational Health, Great Britain. Complies with EU Directive 2004/42/EC: subcategory j.
Availability:	Part of Group Assortment. Local availability subject to confirmation.
PHYSICAL CONSTANTS:	
Shade nos/Colours:	10500* / Grey.
Finish:	Semi-gloss
Volume solids, %:	100
Theoretical spreading rate:	3.3 m ² /l [132.3 sq.ft./US gallon] - 300 micron/12 mils
Flash point:	100 °C [212 °F]
Specific gravity:	1.3 kg/litre [11.2 lbs/US gallon]
Surface dry:	12 approx. hour(s) 20°C/68°F
Dry to touch:	24 hour(s) 20°C/68°F
Fully cured:	7 day(s) 20°C/68°F
VOC content:	9 g/l [0.1 lbs/US gallon] <i>*other shades according to assortment list.</i>
	<i>The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.</i>
APPLICATION DETAILS:	
Version, mixed product:	35530
Mixing ratio:	BASE 35539 : CURING AGENT 95530 3 : 1 by volume Stir CURING AGENT before adding it to the BASE.
Application method:	Airless spray / Brush
Thinner (max.vol.):	Do not dilute. (Consult the separate APPLICATION INSTRUCTIONS)
Pot life:	1 approx. hour(s) 20°C/68°F (Consult the separate APPLICATION INSTRUCTIONS)
Nozzle orifice:	0.019 - 0.031 "
Nozzle pressure:	>250 bar [>3625 psi] (Airless spray data are indicative and subject to adjustment)
Cleaning of tools:	HEMPEL'S TOOL CLEANER 99610
Indicated film thickness, dry:	300 micron [12 mils] see REMARKS overleaf
Indicated film thickness, wet:	300 micron [12 mils]
Recoat interval, min:	According to separate APPLICATION INSTRUCTIONS
Recoat interval, max:	According to separate APPLICATION INSTRUCTIONS
Safety:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.



HEMPADUR MULTI-STRENGTH 35530

SURFACE PREPARATION:	<p>New steel: Remove oil and grease etc. thoroughly with suitable detergent. Remove salts and other contaminants by high pressure fresh water cleaning. Abrasive blasting to near white metal Sa 2½ (ISO 8501-1:1988) with a surface profile corresponding to Rugotest No. 3, BN10a, Keane-Tator Comparator 3.0 G/S, or ISO Comparator Rough Medium (G). Apply immediately after cleaning. All damage of shopprimer and contamination from storage and fabrication should be thoroughly cleaned prior to overcoating.</p> <p>Repair and maintenance: Remove oil and grease etc. thoroughly with suitable detergent. Remove salts and other contaminants by high pressure fresh water cleaning. Old steel surfaces having been exposed to salt water, excessive amounts of salt residues in pittings may call for abrasive blasting, high pressure fresh water hosing, drying, and finally, dry abrasive blasting again.</p> <p>Concrete: Remove slip agent and other possible contaminants by emulsion washing followed by high pressure hosing with fresh water. Remove scum layer and loose matter to a hard, rough and uniform surface, preferably by abrasive blasting, possibly by other mechanical treatment or acid etching. Seal surface with suitable sealer, as per relevant painting specification.</p>
APPLICATION CONDITIONS:	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. Use only where application and curing can proceed at temperatures above: 10°C/50°F. The temperature of paint itself should be 15°C/59°F or above. In-can temperature of the paint should preferably be below 25°C/77°F. Curing requires a relative humidity of: maximum 85%. For application in warm climates, HEMPADUR MULTI-STRENGTH 45751 may preferably replace HEMPADUR MULTI-STRENGTH 35530 as a heavy duty coating. For potable water tanks and pipes please check local product assortment.
PRECEDING COAT	None, or as per specification. Recommended systems are: HEMPADUR 15590 or HEMPADUR SEALER 05990
SUBSEQUENT COAT:	None, or as per specification. Recommended systems are: HEMPADUR or HEMPATHANE
REMARKS:	
Weathering/service temperatures:	The natural tendency of epoxy coatings to chalk in outdoor exposure and to become more sensitive to mechanical damage and chemical exposure at elevated temperatures is also reflected in this product.
Film thicknesses/thinning:	May be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate and may influence drying time and recoating interval. Normal range dry is: 200-300 micron/8-12 mils
Recoating note:	Stir the individual BASE and CURING AGENT thoroughly before mixing and again after mixing until a uniformly coloured mixture is obtained. If colour stability is requested for exposure to sunshine, it is recommended to topcoat with eg HEMPATHANE TOPCOAT 55210. Potable water tanks: See APPLICATION INSTRUCTIONS, as to time before taking into use and post treatment of coated surfaces to be in contact with potable water.
Note:	HEMPADUR MULTI-STRENGTH 35530 For professional use only.
ISSUED BY:	HEMPEL A/S 3553010500

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.